

EFDEDUR

System-Structurecoat GS9161

- Two component structure paint with solvent
- On powder coating co-ordinated system
- Standard-System: GS1061 EFDEDUR-Structure Paint
- Silicone-free
- Fast drying
- Indoor usage
- For structure effects in a processing step orange peeling and two processing steps splatter effect
- Adhesion on not iron metal

Technical / physical data	Resin/ binder	acryl resin to be hardened with isocyanate
	Colour	between powder coating and RAL-Colour, RAL 840 HR
	Gloss value	after powder sample
	Original viscosity	4000 to 5000 mPa.s / Spindel 1 Haake-Viscotester VT02
	Mixing ratio by weight	6 : 1
	Hardener-Typ base	EFDEDUR-Hardener HU0001 polyisocyanate see „Special remarks“
	Potlife after hardener addition	approx. 6 h / 20 °C
	Thinner	EFD-Thinner 400320 EFD-Thinner 400500
	Density after hardener addition, calculated	1,3 g / ml + / - 0,1
	Solid content after hardener addition, calculated	68,8 % + / - 2
	Solid content in volume after hardener addition, calculated	380 ml / kg + / - 10
	Material usage calculated after hardener addition in original viscosity, without application loss	170 to 200 g / m ² dry film thickness 60 to 80 µm

Storability	Approx. 18 month in original packings at an ambient temperature of 5 to 25 °C, in case the original packings are tightly closed. Opened packing must be used very shortly. The minimum storage stability of each batch is mentioned on the product label. A storage time beyond the mentioned date doesn't necessarily mean that the material is unusable. In this case a check of the qualities which are important for the respective.
--------------------	--

Processing and application

Application

Components are to be mixed homogeneously (e.g. with high-speed mixer).
Suited application methods are: high pressure, low pressure and airless spraying

After hardener addition adjust the viscosity acc. to the selected application procedure.

The application has to be done in two spraying passes:

- 1) smooth surface
after a drying time (surface drying) of approx 30 min. / 20 °C
- 2) splatter the required effect appearance on the painted surface,
for this splattering the spraying pressure has to be reduced

Different effects can be achieved by modifying of spraying viscosities,
spraying pressure, as well as by using different nozzle-sizes.

electrostatic-spraying: possible
by roller/ brush: in original viscosity after hardener addition

Substrates

steel: single layer coat
non ferrous metal: lock at Special remarks
plastics, wood: primer necessary

Pretreatment

The substrate must be free of materials which prevent adhesion, e.g. oil, grease,
dust and surfactant. According to the requirements we recommend to apply the
suited chemical (e.g. phosphatizing, chromating) or / and mechanical (e.g. shot
blasting) pretreatment.

Proposal for a coating system

substrate: non ferrous metal, e.g. Aluminium
primer: FREIPOX-Primer ER1912
top coat: EFDEDUR-System-Structurecoat GS9161

Application temperature

above 10 °C

Drying

air drying at 20°C

dust dry:	after 30 min.	(degree of drying 1/ DIN 53150)
dry to touch:	after 5 h	(degree of drying 4/ DIN 53150)
complete dry:	after 8 days	(swinging beam hardness/ ISO 1522)
oven drying:	to 100°C possible	(object temperature)

Cleaning of working equipment

EFD-Thinner 400500

Advise for safety protection and protection of health

The usual precautionary measures for ventilation as well as for personal protection are to be
observed when handling painting materials. Detailed information about dangerous goods, safety
data and recommendations concerning health protection and environment protection can be read in
the corresponding safety data sheet.

Special remarks

Information about Hardener and Thinner:

The hardener and the thinner mentioned on page 1 are stated as standard components for this paint system. The standard hardener is also written in the order documents as well as on the label. Furthermore there are additional hardeners and thinners, which can be used as alternative in case the standard components doesn't meet the requirements. These products are tailor-made e.g. faster or slower hardening.

Hardener are taking influence on the gloss (see page 1).

Test condition

The statements concerning efficiency, drying and caution labelling depend on colour shade. The values mentioned in this data sheet are based on GS9161HD2015, calcit white, satin glossy adjustment and hardening with HU0001.

All information is based on a standard climate 20/65 DIN 50014.

For the calculation of the practical consumption loss additions have to be considered. Indications to this are the practical experience and advices given in DIN 53220.

All information are based on our product knowledge and experience. To the application we have no direct influence. For further information please don't hesitate to contact us.

The information mentioned herein are reference values and are not given as specification.